Pyrotek.

217IP

REAPOR®

eco-friendly sound absorber for challenging environments

Reapor[®] acoustic panels are high-performance noise absorbers that look like cut stone.

It is constructed from small aerated granules made from recycled glass. The granules are fused together through a patented high-temperature sintering process to form a hard, lightweight, fibre-free, non-combustible stone-like panel that can be used indoors and outdoors. The unique material is highly porous, absorbing noise both between and within the granules.

Reapor® panels are simple and easy to install using recommended adhesives (refer to the Reapor® Installation Guide for details). The panels can be cut, drilled and routered using standard woodworking tools, enabling easy installation around obstacles.

The panels are suitable for use outdoors. Wet panels will drain freely and dry in the sun; however, this may result in efflorescence where crystalline salts are deposited on the surface of the panel. Efflorescence will not affect acoustic performance. If efflorescence does occur, the salts may be removed using commercial efflorescence cleaners. (*Please refer to the Reapor® Installation Guide for more information*).

VOC STATEMENT

Reapor[®] does not contain any Volatile Organic Compounds (VOC) when evaluated to the differing definitions as applied under the Australia National Pollutant Inventory, the EU Council Directive 1999/13/EC or the USA EPA Regulation 40CFR 51.100(s). This product can be classed as low VOC-emitting. The material emissions are less than the threshold of 0.5 mg/m²/hr as specified in Green Building Council of Australia 'Green Star' credit IEQ-13. Formaldehyde compound emission rate is less than the threshold of 0.1 mg/m²/hr as specified in 'Green Star' credit IEQ-14.

SPECIFICATIONS

Colour	Light grey	
Available	25 x 625 x 625 mm 25 x 625 x 1200 mm	
	50 x 625 x 625 mm 50 x 625 x 1250 mm	
	63 x 625 x 625 mm	
	Custom sizes available depending on MOQ	

25 mm thick Reapor® does not feature chamfered edges.

Reapor® is a registered trademark of Liaver used with permission for Pyrotek as distributors.



applications

- Rail and motorway tunnels, vent shafts and noise barriers
- Outdoor cafes, bars and restaurants
- Interior walls and ceilings of offices, retail spaces, hospitals, schools and aged care facilities
- Fire exits and stairwells
- HVAC and genset plant rooms
- Industrial noise enclosures
- Shooting ranges

features

- Resists weather, water and UV exposure over an extended period
- Non-combustible
- Exceptionally high NRC of 0.95 (50 mm thick panel)
- Easy to cut, drill and rout using standard woodworking tools
- Natural 'stone-like' appearance to suit indoor and outdoor designs
- Made from recycled glass
- Lightweight
- Fibre free

2171F

PRODUCT SPECIFICATIONS

Product name	Thickness (mm)	Panel size			Density
		Length (mm)	Width (mm)	Approximate weight (kg)	(kg/m ³)
Reapor® 25/625625	25	625		2.6	
Reapor® 25/1200625	25	1200		5.1	
Reapor® 50/625625	50	625	625	5.3	270
Reapor [®] 50/1250625	50	1250		10.5	
Reapor® 63/625625	63	625		6.6	

 $\textit{Tolerances: Dimensions \pm 1 mm, Density: \pm 10\%. 25 mm thick Reapor^{\circ} does not feature chamfered edges.}$

MATERIAL PROPERTIES

Test method	Property	Report	Results	
DIN 196-1	Compressive strength		1.46 N/mm² (±10%)	
	Flexural strength	D 10 16 100 01	0.53 N/mm² (±10%)	
DIN 1607	Tensile strength	B 12.16.103.01	0.14 N/mm² (±10%)	
DIN 1048	Dynamic modulus of elasticity		833 N/mm² (±10%)	
DIN 52612	Thermal conductivity	1254P41/P	0.077 W/mK	
AS/NZS 3000	Electrical conductivity	9765	Non-conductive	
EN 13501-1	Fire classification of construction products and building materials	KB 3.1/11-121-3	Non-combustible	
DIN 4102	Fire resistance	16-900 9171 002-1		
AC 1520 1 (JCO 1102	Fire resistance	FNC11639		
AS 1530.1 / ISO 1182	Fire resistance (as a system with Pyrotek CB Adhesive)	FNC11641		
	Method for fire tests on building materials, components and structures	16-000832	Ignitability	0
AC 1520.2			Spread of flame	0
AS 1530.3			Heat evolved	0
			Smoke developed	1
ISO 5660 / AS/NZS 3837	Building code compliance	FH 5964-TT	NCC	1
			NZBC	1-S
ASTM D5116	Total volatile organic compound emission rate	0./120020	0.026 mg/m²/hr	
	Formaldehyde compound emission rate	CV130829	<0.005 mg/m²/hr	



Pyrołek.

TECHNICAL DATA SHEET

217IP

ACOUSTIC PERFORMANCE

Frequency (Hz)	Reapor 25 mm	Reapor 50 mm	Reapor 63 mm
100	0.04	0.08	0.16
125	0.06	0.10	0.23
160	0.08	0.29	0.38
200	0.13	0.37	0.53
250	0.13	0.57	0.81
315	0.23	0.92	1.02
400	0.35	1.12	1.13
500	0.52	1.23	1.13
630	0.67	1.21	1.07
800	0.90	1.02	0.97
1000	1.05	0.98	0.92
1250	1.13	1.03	0.98
1600	1.05	1.09	1.04
2000	0.97	1.08	1.02
2500	0.93	1.04	1.03
3150	0.98	1.05	1.01
4000	0.99	1.04	1.08
5000	0.94	1.04	0.95
NRC	0.65	0.95	0.95
SAA	0.67	0.97	0.97
aw	0.45 (MH)	0.90	1.00



Tested to ISO 354:2003 at Vienna Experimental and Research Institute (Austria) & CSIRO (Australia) Report Numbers: MA 39-VFA 2007-1277.01, AC186-01-1 & P-BA 195/2017e

For further information and contact details, please visit our website pyroteknc.com Caveats: Specifications are subject to change without notice. The data in this document is typical of average values based on tests by independent laboratories or by the manufacturer and are indicative only. Materials must be tested under intended service conditions to determine their suitability for purpose. The conclusions drawn from acoustic test results are as interpreted by qualified independent testing authorities. Nathing here releases the purchaser/user from responsibility to determine the suitability of the product for their project needs. Always seek the opinion of your acoustic mechanical and fire engineer on data presented by the manufacturer. Due to the wide variety of individual projects, Pyrotek is not responsible for differing outcomes from using their products. Pyrotek disclaims any liability for damages or consequential loss as a result of reliance solely on the information presented. No warranty is made that the use of this information or of the products, processes or equipment to which this information Page refers will not infringe any third party's patents or rights. DISCLAIMER: This document is covered by Pyrotek standard Disclaimer, Warranty and © Copyright clauses. See pyrotek.com/disclaimer.

